


What is claimed is:


1. A photothermographic material comprising a support, an organic silver salt, a light-sensitive silver halide, a reducing agent and a contrast-increasing agent, wherein the photothermographic material further comprises a secondary or tertiary amino group-containing alkoxy silane compound and a polyethyleneimine.

2. The photothermographic material of claim 1, wherein said alkoxy silane compound is represented by the following formula (1a) or (1b):

Formula (1a)



Formula (1b)



wherein X and Y are each a straight chain or branched bivalent saturated hydrocarbon group having 1 to 10 carbon

atoms; R_1 , R_2 , R_5 and R_6 are each a straight chain or branched saturated hydrocarbon group having 1 to 4 carbon atoms; R_3 and R_4 are each a hydrogen atom, an aliphatic group having 1 to 20 carbon atoms or an aromatic group, provided that at least one of R_3 and R_4 is an aliphatic group having 1 to 20 carbon atoms or an aromatic group, or R_3 and R_4 combine with each other to form a ring; m and o are each 0 or 1, n and p are each 2 or 3.

3. The photothermographic material of claim 1, wherein the photothermographic material is provided on one side of the support with an image forming layer and a protective layer and on the other side of the support with a backing layer and a backing protective layer.

4. The photothermographic material of claim 3, wherein the image forming layer or the protective layer contains said alkoxysilane compound at 100 to 1000 mg/m².

5. The photothermographic material of claim 3, wherein the backing layer or the backing protective layer contains said polyethyleneimine at 1 to 100 mg/m².

6. The photothermographic material of claim 3, wherein the image forming layer or the protective layer contains said alkoxysilane compound at 100 to 1000 mg/m², and the backing layer or the backing protective layer contains said polyethyleneimine at 1 to 100 mg/m².

7. The photothermographic material of claim 3, wherein the image forming layer or the protective layer contains said alkoxysilane compound at 100 to 1000 mg/m² and said polyethyleneimine at 1 to 100 mg/m².

8. The photothermographic material of claim 3, wherein the backing layer or the backing protective layer contains said alkoxysilane compound at 100 to 1000 mg/m² and said polyethyleneimine at 1 to 100 mg/m².

9. A package of a rolled photothermographic material, wherein the package comprises a rolled photothermographic material in which a photothermographic material as claimed in claim 1 is wound on a light-shielding roll core, a light-shielding flange member provided at both ends of the roll core and a light-shielding leader which is attached to the top of the photothermographic material and has a width

greater than that of the rolled photothermographic material and a prescribed length of the light-shielding leader is wound around the rolled photothermographic material with covering a circumferential portion of the flange so that light-shielding is performed with maintaining an internal absolute humidity at 4 to 17 g/m² under an environment of 10 to 25 °C.

10. The package of claim 9, wherein said light-shielding leader exhibits a moisture permeability at 40 °c and 90% RH of 5 g/m²·24 hr or less.

11. The package of claim 9, wherein said core has a moisture content of 4% by weight or less.

12. The package of claim 9, wherein the photographic material is rolled on the core in an atmosphere of an absolute humidity of 5 to 15 g/m² and a temperature of 10 to 30 °C.